

## **Technical Data Sheet**

## Arsapylene N. GF-I 11351 332610010340

Product Type: Reinforced polypropylene for injection molding.

Product Description: Arsapylene N. GF-I 11351 is a natural color 30% reinforced glass fiber

Polypropylene designed for injection molding process. The product provides an excellent balance of

mechanical & processability and features as high long-term heat-stability.

General		
Material	Polypropylene Reinforced with glass fibers	
Process Method	• Injection	
Color	Natural	

Physical	Test Method	Test Condition	Value	Unit
Density	ASTM D792	23 °C	1.1	gr/cm³
Ash/Filler	ASTM D5630	600 °C	30	%
Mechanical	Test Method	Test Condition	Value	Unit
Tensile Strength at Break	ASTM D638	5 mm/min	80	MPa
Tensile Strain at Break	ASTM D638	5 mm/min	4	%
Izod Impact Strength	ASTM D256	Notched at 23°C	15	kJ/m²

All mentioned information in this technical data sheet present current knowledge and experience of Arsam Lab.
Naturally, these data do not guarantee certain values since may vary on customers processing conditions, so they are provided for reference purposes only and should not be used alone to create specification limits and design basis.

## **Processing Conditions:**

- Recommended Zone Setting are as follows: (200-230) °C
- Mold Surface Temperature: (50-65)°C
- Pre-drying is necessary for materials and dryer operation at 80 °C is recommended.
- Drying time 1-2 hour is generally sufficient.

Tel: +98-21-65435841-2 | Fax: +98-21-26213985 www.arsamplast.com | E-mail: arsam.secretary@riseco.co