

## Technical Data Sheet

### Arsapylene CC-I 11038

**Product Type:** reinforced polypropylene externally lubricated for injection moulding.

**Product Description:** Arsapylene CC-I 11038 is polypropylene filled with 30% calcium carbonate by good mechanical properties, dimensional stability and stiffness. This compound is used in electrical, housewares and other utility products. This grade is designed to be processed in injection molding techniques.

Property	Test Method	Test Condition	Value	Unit
<b>General Properties</b>				
Material	polypropylene filled with 30% calcium carbonate			
Process Method	Injection			
Color	White			
<b>Physical Properties</b>				
Density	ASTM D 792	(23 °C)	1.1	g/cm <sup>3</sup>
Ash/Filler/ TD Content	ASTM D 5630	(600 °C)	30	%
Mold Shrinkage	ASTM D 955	24 Hr	-	%
Melt Flow Index	ASTM D 1238	230 °C-2.16 kg	4.7	gr/10min
<b>Mechanical Properties</b>				
Tensile Strength at Break	ASTM D 638	(50 mm/min)	18	MPa
Tensile Strength Yield	ASTM D 638	(50 mm/min )	19	MPa
Tensile strain at Break	ASTM D 638	(50 mm/min )	120	%
Tensile strain at Yield	ASTM D 638	(50 mm/min )	5.1	%
Izod Impact Strength	ASTM D 256	Notched at 23°C	21	KJ/m <sup>2</sup>

- All mentioned information in this technical data sheet present current knowledge and experience of Arsam. Naturally, these data do not guarantee certain values since may vary on customers processing conditions, so they are provided for reference purposes only and should not be used alone to create specification limits and design basis.

**Processing Conditions:**

- Recommended Zone Setting are as follows: (190-220) °C
- Mold Surface Temperature: (40-60 ) °C